

# H630 CSM

16/07/2014



## CSM 60 SHEETING: FOR TECHNICAL APPLICATIONS

### FEATURES

High grade chlorosulphonated polyethylene (CSM).

### ADVANTAGES

- Good resistance to diluted and low oxidant acids
- Excellent oxidation, weather and ozone resistance
- Very good high temperature resistance
- Excellent resistance to hydrocarbonated solvents
- Resistant to alcohols and most inorganic chemical products
- Moderate resistance to aliphatic and aromatic hydrocarbons
- Matte finish to guarantee a good surface finished quality, to secure an easy unrolling, and to facilitate adhesive bonding processes

### BENEFITS

- Performance
- Service life
- Safety


### APPLICATIONS

Gaskets or washers cutting and manufacturing of pieces for general purpose applications in contact with:

- water
- diluted and low oxidant acids

[www.trelleborg.com/elastomerlaminates](http://www.trelleborg.com/elastomerlaminates)

## MECHANICAL, PHYSICAL AND CHEMICAL PROPERTIES

Measured characteristics		Standard	Value	
<b>MECHANICAL</b>				
<i>Rubber compound - black</i>			CSM 	
<i>Density</i>			1.30 ± 0.05	g/cm <sup>3</sup>
<i>Hardness</i>		ASTM D2240	60 ± 5	Shore A
<i>Tensile strength</i>		ISO 37	≥ 9	MPa
<i>Elongation at break</i>		ISO 37	≥ 350	%
<i>Tear resistance</i>		ISO 34-1	≥ 20	N/mm
<i>Compression set after 22 h at 70 °C</i>		ISO 815-1	≤ 35	%
<b>TEMPERATURE</b>				
<i>Working temperature</i>			- 35/+ 125	°C
<b>AGEING</b>				
<i>Δ Hardness after 168 h at 70 °C</i>		ASTM D573	≤ 5	Shore A
<i>Ozone resistance, 200 pphm, 48 h, 30 °C, 20 %</i>		ASTM D1149 type A	No crack	
<b>OIL RESISTANCE</b>				
<i>Oil IRM 903, Δ volume after 70 h at 70 °C</i>		ASTM D471	≤ 40	%
<b>CHEMICAL RESISTANCE</b>				
<i>Diluted acids and bases</i>	<i>Concentrated acids and bases</i>	<i>Ozone</i>	<i>Oils and hydrocarbons</i>	
<b>Very good</b>	<b>Good</b>	<b>Very good</b>	<b>Good</b>	

### DIMENSIONS

Thickness (mm)		Width (mm)		Length (m)		Weight (kg/m <sup>2</sup> )	Sides finish
2	± 0.3	1400	± 2 %	15	± 2 %	2.60	2 sides matt
3	± 0.3	1400	± 2 %	10	± 2 %	3.90	2 sides matt
4	± 0.4	1400	± 2 %	10	± 2 %	5.20	2 sides matt
5	± 0.4	1400	± 2 %	10	± 2 %	6.50	1 side smooth/1 side matt
6	± 0.5	1400	± 2 %	10	± 2 %	7.80	1 side smooth/1 side matt

### IDENTIFICATION

<i>Branding</i>	Without.
<i>Packaging</i>	Thickness ≤ 6 mm rolled on cardboard tube Ø 80 mm. Thickness > 6 mm in roll.
<i>Wrapping</i>	Black polyethylene film.
<i>Labelling</i>	Self-adhesive label indicating product name, dimensions, area in m <sup>2</sup> , nominal weight, and product code to allow product traceability.