

NBR SBR

16/07/2014



NITRILE SHEETING: BASIC QUALITY

FEATURES

Basic quality level NBR.

ADVANTAGES

- Medium resistance to hydrocarbons
- Good ratio quality/price

BENEFITS

• Economy

APPLICATIONS

Gaskets or washers cutting and manufacturing of pieces for general purpose applications in contact with oils and hydrocarbons.

No resistance to petrol, oxygenated fuel, domestic gas.

www.trelleborg.com/elastomerlaminates

MECHANICAL, PHYSICAL AND CHEMICAL PROPERTIES

	Measured characteristics	Standard	Value			
MECHANICAL						
	Rubber compound - black		NBR/SBR			
	Density		1.50 ± 0.05	g/cm ³		
	Hardness	ASTM D2240	65 ± 5	Shore A		
	Tensile strength	ISO 37	≥4	MPa		
	Elongation at break	ISO 37	≥ 250	%		
	Tear resistance	ISO 34-1	≥ 15	N/mm		
Comp	pression set after 22 h at 70 °C $$	ISO 815-1	≤45	%		
TEMPERATURE						
	Working temperature		- 25/+ 90	°C		
AGEING						
Δ	A Hardness after 70 h at 70 °C	ASTM D573	≤5	Shore A		
Δ Tensi	ile strenght after 70 h at 70 °C	ASTM D573	≤-15	%		
Δ Elongatio	on at break after 70 h at 70 °C	ASTM D573	≤-40	%		
OIL RESISTANCE						
Oil IRM 901	, Δ volume after 70 h at 70 °C	ASTM D471	≤25	%		
CHEMICAL RESISTANCE						
Diluted acids and bases	Concentrated acids and bases	Ozone	Oils and hydrocarbons			
Medium	Non suitable	Medium	Medium			

DIMENSIONS

	kness 1m)		dth m)		ngth n)	Weight (kg/m²)	Sides finish	Option (ply)
1	± 0.3	1400	±2%	20	±2%	1.5	2 smooth sides	
1.5	± 0.3	1400	±2%	15	±2%	2.25	2 smooth sides	
2	± 0.3	1400	±2%	15	±2%	3	2 smooth sides	1P
3	± 0.3	1400	±2%	10	±2%	4.5	2 smooth sides	1 P
4	± 0.4	1400	±2%	10	±2%	6	2 smooth sides	2P
5	± 0.4	1400	±2%	10	±2%	7.5	2 smooth sides	2P
6	± 0.5	1400	±2%	10	±2%	9	2 smooth sides	
8	± 0.7	1400	±2%	5	±2%	12	2 smooth sides	
10	± 1.0	1400	±2%	5	±2%	15	2 smooth sides	

IDENTIFICATION

Branding	Without.			
Packaging	Thickness \leq 6 mm rolled on cardboard tube Ø 80 mm. Thickness > 6 mm in roll.			
Wrapping	Black polyethylene film.			
Labelling	Self-adhesive label indicating product name, dimensions, area in m ² , nominal weight, and product code to allow product traceability.			