



# YELLOWFINE NR

16/07/2014



## MEDIUM WEAR SHEETING: FINE GRAIN SIZE MATERIAL

### FEATURES

Wear resistant natural rubber, yellow.

### ADVANTAGES

- Excellent mechanical properties: tensile strength, elongation at break, tear resistance, abrasion, etc.
- Excellent resistance to fine grain size products projection and fretting wear: sand, shot blasting, fine particles, abrasive dust, etc.
- Corrosion protection
- Noise and vibration propagation reduction
- Possibility to be produced with bonding layer for cold vulcanizing or with steel backing for mechanical fixing

### BENEFITS

- Performance
- Safety
- Reliability
- Service life

### APPLICATIONS

Hoppers, chutes, operating cyclones, vibrating lines, silos, etc., linings to protect equipment against very abrasive fine grain size products wear, due to their very nature (rock, wood, metal, all fine particle size materials, chemical products, etc.), density and hardness (medium to high), forms (fine particles, bulks, etc.), with dry conditions and maximum temperature + 70 °C.

Manufacturing of rubber skirts.

Hanging panels fostering materials cleaning and removal.

Areas of activity: sand and gravel quarries, aggregate and cement industries, concrete plants, etc.

[www.trelleborg.com/elastomerlaminates](http://www.trelleborg.com/elastomerlaminates)

## MECHANICAL, PHYSICAL AND CHEMICAL PROPERTIES

	Measured characteristics	Standard	Value	
<b>MECHANICAL</b>				
	<i>Rubber compound - yellow</i>		NR R491	
	<i>Density</i>		1.05 ± 0.05	g/cm <sup>3</sup>
	<i>Hardness</i>	ASTM D2240	45 ± 5	Shore A
	<i>Tensile strength</i>	ISO 37	≥ 16	MPa
	<i>Elongation at break</i>	ISO 37	≥ 600	%
	<i>Tear resistance</i>	ISO 34-1	≥ 25	N/mm
	<i>Abrasion resistance (5 N)</i>	ISO 4649	≤ 83	mm <sup>3</sup>
	<i>Compression set after 22 h at 70 °C</i>	ISO 815-1	≤ 30	%
<b>TEMPERATURE</b>				
	<i>Working temperature</i>		- 40/+ 85	°C
<b>AGEING</b>				
	<i>Δ Hardness after 70 h at 70 °C</i>	ASTM D573	≤ 5	Shore A
	<i>Δ Tensile strenght after 70 h at 70 °C</i>	ASTM D573	≤ - 15	%
	<i>Δ Elongation at break after 70 h at 70 °C</i>	ASTM D573	≤ - 25	%
<b>CHEMICAL RESISTANCE</b>				
<i>Diluted acids and bases</i>	<i>Concentrated acids and bases</i>	<i>Ozone</i>	<i>Oils and hydrocarbons</i>	
<b>Very good</b>	<b>Good</b>	<b>Medium</b>	<b>Non suitable</b>	

## DIMENSIONS

Thickness (mm)	Width (mm)	Length (m)	Weight (kg/m <sup>2</sup> )	Sides finish	Option (bonding layer)	
3	± 0.3	1400 ± 2 %	10 ± 2 %	3.15	2 smooth sides	
4	± 0.4	1400 ± 2 %	10 ± 2 %	4.20	2 smooth sides	
5	± 0.4	1400 ± 2 %	10 ± 2 %	5.25	2 smooth sides	
6	± 0.5	1400 ± 2 %	10 ± 2 %	6.30	2 smooth sides	
8	± 0.7	1400 ± 2 %	10 ± 2 %	8.40	2 smooth sides	
10	± 1.0	1400 ± 2 %	10 ± 2 %	10.50	2 smooth sides	
12	± 1.0	1400 ± 2 %	5 ± 2 %	12.60	2 smooth sides	
15	± 1.0	1400 ± 2 %	5 ± 2 %	15.75	2 smooth sides	
20	± 1.4	1400 ± 2 %	5 ± 2 %	21.00	2 smooth sides	

## IDENTIFICATION

<i>Branding</i>	Without.
<i>Packaging</i>	Thickness ≤ 6 mm rolled on cardboard tube Ø 80 mm. Thickness > 6 mm in roll. Bonding layer internal side protected by a white polypropylene film, easily removable by hand.
<i>Wrapping</i>	Black polyethylene film.
<i>Labelling</i>	Self-adhesive label indicating product name, dimensions, area in m <sup>2</sup> , nominal weight, and product code to allow product traceability.